



Derby Gaskets Ltd

SPECIALISTS IN SEALING TECHNOLOGY

Units 2, 3, & 4 Racecourse Ind. Park,
Mansfield Road,
Derby DE21 4SX

Tel: 01332 360701, Fax: 01332 291484

www.derbygaskets.com



GB 19386

MATERIAL SPECIFICATION

NEOPRENE SPONGE CORD Based upon 3mm dia.

Diameter tolerance:	+/- 0.35mm
Weight:	approx. 5g per mtr
Density:	160 kg per cu.mtr
Linear shrinkage 22 hrs at 70C measured after 1 hour recovery at room temperature:	5%
Resistance to UV, 48 hrs:	no cracking
Water absorption:	5% max.
Swelling in ASTM fuel type b weight change:	not tested

We reserve the right to alter the specification without notice. Values given may vary according to manufacturing tolerances. It is the responsibility of the purchaser to ensure material is suitable for purpose and we will provide samples for test if required.

DGL-MSS38 Iss 2

Registered Office: Derby Gaskets Ltd; Units 2, 3 & 4 Racecourse Industrial Park, Mansfield Road, Derby, DE21 4SX
Chairman: C. Prince, Directors: S. Prince (Managing), Y. Kennedy (Company Secretary).
VAT 295 2969 03. Co. Reg. 1914526