



Derby Gaskets Ltd

SPECIALISTS IN SEALING TECHNOLOGY

Units 2, 3, & 4 Racecourse Ind. Park,
Mansfield Road,
Derby DE21 4SX

Tel: 01332 360701, Fax: 01332 291484

www.derbygaskets.com



GB 19386

MATERIAL SPECIFICATION

SILICONE SPONGE

Quality:	Commercial	
Density:	16 lbs/cu.ft (Sil 16)	
Elongation:	N/A	
Compression set: (150C for 70 hours) Recovery period 48 hours 25% compression	6%	Test method BS4443 part 1 method A
Resistance to heat ageing: (after 168 hrs at 150C) Compression set (150C for 70 hours) Recovery period 48 hours 25% compression	5%	Test method BS4443 part 1 method A
Operating temperature:	-60C to +200C	

We reserve the right to alter the specification without notice. Values given may vary according to manufacturing tolerances. It is the responsibility of the purchaser to ensure material is suitable for purpose and we will provide samples for test if required.

DGL-MSS63 Iss 2

Registered Office: Derby Gaskets Ltd; Units 2, 3 & 4 Racecourse Industrial Park, Mansfield Road, Derby, DE21 4SX
Chairman: C. Prince, Directors: S. Prince (Managing), Y. Kennedy (Company Secretary).
VAT 295 2969 03. Co. Reg. 1914526